

Power wallpaper paste Special Vinyl

Instructions for use: Power Paste Special is suitable for pasting woodchip wallpapers, paper wallpa-

pers, vinyl wallpapers and similar wall coverings.

Technical specifications: Components: Starch ether, methylcellulose, polyvinyl acetate

powder

Apparent weight: approx. 0.50 g/cm³

pH-value: approx. 8

Solubility: ready for use after approx. 30 minutes

Usage: approx. 200 ml/m²

Surface preparation: The surface must be dry, firm, and dust and grease-free. Remove old, peeling

wallpapers and distempers using decotric Wallpaper Remover. Make good cracks and holes using decofill Interior or decomur Super Bonding Filler. Pretreat highly absorbent, sanding and chalking surfaces using decotric Deeply Penetrating Primer – Solvent Free. Water-soluble contaminations in the surface, which could show through when wallpapered over, should be isolated using decotric Insulating Spray. We recommend a first coat with decotric Wallpaper Primer white if hanging highly translucent wallpapers and where surfaces are

highly contrasting.

Application: Vigorously stir Power Paste Special into clean, cold water and continue to stir

for a short time. Leave to mature for approx. 30 minutes and then stir well

again.

Evenly apply the adhesive to the wallpaper using a brush. Fold the pasted ends

inwards and hang after an adequate soaking time.

We recommend to add 750 g decotric Wallpaper and Border Adhesive per 200 g packet decotric Power Paste Special for use on hardly absorbent surfaces and

to increase the moisture resistance.

Hang the wallpaper according to the manufacturer's instructions.

Do not use if the surface and room temperature are below + 5° Celsius!

Remove adhesive residues using a damp cloth.

Clean tools in water after use.

Mixing ratio:

for	Mixing ratio	Quantity of water per 200-g packet	Coverage of a 200-g packet
Pre-pasting	1:50	10	60-80 m²
Woodchip, vinyl, embossed and other heavyweight wall-paper	1:20	4	20-25 m²

Storage: Store in a cool and dry place!

Available size: 200 g collapsible box 023201126

Minimum durability: 5 years as of date of manufacture